

AMBLYGON TA 30-1, TA 30-2

Special greases for long-term lubrication and high temperatures



Benefits for your application

- Good resistance to ambient media, water and water steam
- Good corrosion protection
- Good adhesion
- Good sealing effect
- Suitable up to 160 °C

Description

AMBLYGON TA 30/1 and TA 30/2 are long-term and high-temperature lubricating greases based on mineral oil and polyurea.

These lubricating greases are used for long-term lifetime lubrication in the machine-building sector covering a wide service temperature range up to 160 °C. AMBLYGON TA 30/1 and TA 30/2 offer good adhesion, resistance to hot water and diluted alkaline and acid solutions. AMBLYGON TA 30/1 and TA 30/2 are resistant to oxidation and ageing and protect against corrosion.

Application

AMBLYGON TA 30/1 and TA 30/2 lubricate bearings and joints subject to high loads and temperatures, for example in:

- conveyors
- rollers in continuous casting machines
- kilns (rotary tubular kilns)
- water pumps
- hot rollers
- tarmac laying machines
- gate valves
- seals
- washing machines and dishwashers

- impact mechanisms in power tools
- wheel bearings, joints, hinges
- king pins
- fully enclosed rolling bearings
- block presses

AMBLYGON TA 30/1 and TA 30/2 are also used in combination with mineral-oil-resistant elastomer seals.

Application notes

Prior to series application we recommend checking compatibility with elastomers, if possible in the component under conditions similar to actual use.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	AMBLYGON TA 30/2	AMBLYGON TA 30/1
Can 1 kg	+	+
Bucket 25 kg	+	+



AMBLYGON TA 30-1, TA 30-2

Special greases for long-term lubrication and high temperatures

Product data	AMBLYGON TA 30/1	AMBLYGON TA 30/2
Article number	020157	020133
Chemical composition, thickener	polyurea	polyurea
Chemical composition, type of oil	mineral oil	mineral oil
Lower service temperature	-20 °C / -4 °F	-15 °C / 5 °F
Upper service temperature	160 °C / 320 °F	160 °C / 320 °F
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	310 x 0.1 mm	285 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	340 x 0.1 mm	315 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 500 mm ² /s	approx. 500 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 32 mm ² /s	approx. 32 mm ² /s
Drop point, DIN ISO 2176, IP 396	>= 220 °C	>= 250 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	60 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG / Geisenhausenerstraße 7 / 81379 München / Germany / phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.