

NOSOL GBY 2

Fully synthetic lubricating and sealing grease for valves and fittings



Benefits for your application

- Good wetting power
- Good water resistance
- Wide service temperature range
- Resistant to town gas, long-distance gas, natural gas and e.g. aliphatic hydrocarbons
- Excellent sealing effect
- Certified acc. to DIN 3536 and DIN EN 377

Description

NOSOL GBY 2 is a fully synthetic lubricating and sealing grease for valves and fittings, especially gas fittings and bearings. It is resistant to water, mineral oil, glycol-water mixtures, gaseous and liquid aliphatic hydrocarbons such as town gas, long-distance gas, natural gas, petroleum gas and their substitute gases as well as to propane and propane-butane mixtures.

Approvals

Tested and approved acc. to DIN 3536 as: "Lubricant for gas fittings in domestic gas installations, gas distribution and transport lines", DIN designation lubricant DIN 3536-10-90 and DIN EN 377 class B.

DIN-DVGW registration number: NG-5161BU0518.

Application

NOSOL GBY 2 is a special lubricating and sealing grease for valves and fittings, coolers, pumping, drilling and dispensing stations and in refineries, chemical and automotive industry.

Application notes

NOSOL GBY 2 can be applied by spatula, brush or other usual lubrication systems.

Friction and lube points should be metallically blank, i.e. free of oils, greases, perspiration and contamination.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	NOSOL GBY 2
Can 1 kg	+
Bucket 25 kg	+

Product data	NOSOL GBY 2
Article number	008044
Chemical composition, type of oil	ester oil
Chemical composition, thickener	silicate
Lower service temperature	-10 °C / 14 °F
Upper service temperature	90 °C / 194 °F
Colour space	beige
Texture	homogeneous
Texture	long-fibred



NOSOL GBY 2

Fully synthetic lubricating and sealing grease for valves and fittings

Product data	NOSOL GBY 2
Density at 20 °C	approx. 1.15 g/cm ³
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	240 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	300 x 0.1 mm
Oil separation, ASTM D 6184 [FTMS 791 C 321], after 30 h/100 °C	<= 0.5 % by weight
Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating	<= 1 - 90
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	24 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.